

Altered State

12x24 Porcelain

mosaic 
Products. Design. Solutions.



03AV3411224U



03AV3421224U



03AV3431224U



03AV3441224U



03AV3451224U



Tile: 6x24 - 12x24 - 24x24

Mosaic: 2x12

Trim: 6x24 Bullnose

For more information
and images:



Altered State

Porcelain



Technical Characteristics

Test Item	Test Method	Test Result
Breaking Strength	ASTM C648	> 500 lbf
Bond Strength	ASTM C482	> 200 psi
Chemical Resistance	ASTM C650	Unaffected
Frost Resistance	ASTM C1026	Resistant
Water Absorption	ASTM C373	< 0.20%
Scratch Hardness	Mohs Scale	7
DCOF	AcuTest	0.42-0.52

Nominal Size	Actual Size	Thickness	Finish	Rectified
6" x 24"	5.79" x 23.5"	10.5 mm	Unpolished	Yes
12" x 24"	11.69" x 23.5"	10.5 mm	Unpolished	Yes
24" x 24"	23.5" x 23.5"	10.5 mm	Unpolished	Yes
2" x 12" Mosaic	1.85" x 11.69" (11.69" x 11.69" sheet)	10.5 mm	Unpolished	-
6" x 24" Bullnose	5.79" x 23.5"	10.5 mm	Unpolished	-

Installation Note: The TCNA recommends rectangular shape tile be installed with maximum of 33% offset in order to resolve any possible lippage from one tile to the next.

