

Casablanca

8x8 or 8x9 Hex Porcelain

mosaic 
Products. Design. Solutions.




For more information
and images:






88CASWHI89HN



88CASWHI8



88CASGRA89H



88CASGRA8



88CASBLA89HN



88CASBLA8



88CASMAR8BN



88CASHER8BN



88CASMAR8N




88CASHER8N






88CASFON8



88CASAQU8





Technical Characteristics

Test Item	Test Method	Test Result
Water Absorption	ASTM C373	< 3%
Breaking Strength	ASTM C648	Min. 250
Scratch Hardness	MOH'S	4
Chemical Resistance	ASTM C650	Unaffected
Frost Resistance	ASTM C1026	Resistant
Minimum Bond Strength (PSI)	ASTM C482	165
Dynamic Coefficient of Friction (DCOF)	ASTM C1028	≥ 0.42
Facial Dimensions	ASTM C499	Pass
Range of Thickness	ASTM C499	Pass
Warpage	ASTM C485	Pass
Wedging	ASTM C502	Pass

Nominal Size	Actual Size	Thickness
8" x 8"	7.87" x 7.87"	8.2 mm
8" x 9" Hexagon	7.87" x 9.06"	8.2 mm



For your convenience, select products are stocked in our Central Service Center.