

Marble Lincoln Suite

12x24 Ceramic Wall



88MARLIN1224S



Wall Tile: 12x24

For more information
and images:





Technical Characteristics

Test Item	Test Method	Required Values	Value
Water Absorption	ASTM C373	≤ 0.5%	≥ 0.5%
Breaking Strength	ASTM C648	≥ 275	≥ 275
Scratch Hardness	MOH's Scale	-	5
Chemical Resistance	ASTM C650	Unaffected	Unaffected
Frost Resistance	ASTM C1026	Resistant	Resistant
Deep Abrasion - Unglazed Tiles	ASTM C1243	< 175 mm³	Pass
Minimum Bond Strength (PSI)	ASTM C482	≥ 50 PSI	165
DCOF	A137.1	≥ 0.42	≥ 0.42
Shade and Texture Rating	CTDA "V"	=	V3
Facial Dimensions	C499	1.5% Max	Pass
Range of Thickness	C499	0.040 Max	Pass
Warpage	ASTM C485	0.75%	Pass
Wedging	ASTM C502	1.0% Max	Pass

Nominal Size	Actual Size	Thickness	Finish	Rectified
12" x 24"	11.81" x 23.62"	7 mm	Lux Matte	Yes